



UDC 66.017+ 66.018

DOI: 10.31643/2021/6445.29



IRSTI 55.09.43

Investigation of the properties of composite materials based on epoxy resins with microsilica additives

Serekpayeva M.A., * Kokayeva G.A., Niyazbekova R.K., Kardybai S.

S. Seifullin Kazakh Agro Technical University, Nur-Sultan, Kazakhstan

** Corresponding author email: GAKokaeva@mail.ru*

ABSTRACT

The outcomes of studying epoxy-based composite materials supplemented with microsilica are provided in the article. Microsilica was used as a filler. The samples were produced on the epoxy ED-20 basis supplemented with 2, 5 and 10 mas. % of microsilica. The structure and size of finely dispersed filler particles were defined. The obtained composites were tested for resistance to the effect of variable temperatures, corrosive, and abrasion. The study outcomes proved that samples supplemented with 2% of microsilica are more resistant to acid and alkali as well as to petrol than those ones supplemented with 25% of microsilica. Besides the amount of the filler from 2 to 10% doesn't sufficiently affect the resistance to variable temperatures. When microsilica is added to epoxy resin, it causes scuff resistance increase. The conducted testing proved that the developed composite materials are resistant to the effect of variable temperatures, corrosive, and abrasion. This enables to use these materials as coatings and anti-corrosion protection during machine maintenance.

Keywords: epoxy resin, microsilica, filled composite material, chemical resistance, composite material, corrosive, abrasion, coating.

Received: 29 June 2021

Peer reviewed: 16 July 2021

Accepted: 06 August 2021

Information about authors:	
Serekpayeva Mira Amangeldinovna	Doctoral student of the Department of Standardization, Metrology and Certification, S. Seifullin Kazakh Agro Technical University, Nur-Sultan, Kazakhstan. E-mail: mika82.02@mail.ru
Kokayeva Gulnara Aitikenovna	Candidate of Technical sciences, Associate professor of the Department of Technological machines and equipment, S. Seifullin Kazakh Agro Technical University, Nur-Sultan, Kazakhstan. E-mail: GAKokaeva@mail.ru, https://orcid.org/0000-0001-9571-5081
Niyazbekova Rimma Kalmanbayevna	Doctor of Technical sciences, Associate professor of the Department of Standardization, Metrology and Certification, S. Seifullin Kazakh Agro Technical University, Nur-Sultan, Kazakhstan. E-mail: rimma.n60@mail.ru, ORCID ID: 0000-0001-8688-1408
Kardybai Sauatbek	Assistant of the Department of Technological machines and equipment, S. Seifullin Kazakh Agro Technical University, Nur-Sultan, Kazakhstan. E-mail: sautbek_kz@mail.ru

Introduction

Technology for applying hardening coating including composite ones plays an important role for upgrading farming machinery, as they contribute to durability of individual elements, parts, and entire machines during their maintenance. Polymer composite materials are used during machines maintenance for restoring the size of worn-out parts, for filling cracks and holes, for reinforcing threaded joints and stationary fits, for anti-corrosion protection, for bonding parts and materials, and also for parts production.

Increasing demands to the quality and rate of equipment repair operations require a wide range of highly-efficient systems capable to restore metal surfaces and different structures damaged from wear, abrasion, blows and corrosion. In this connection, production of composite materials based on epoxy oligomers that are highly adhesive to many materials is relevant and demanded in practice in different spheres.

Polymer matrix for composite material is chosen taking into account the conditions of maintenance. Composite properties depend on the matrix of polymer material. These properties are resistance to corrosive, thermal resistance,

strength, moisture resistance, as well as the method of item production.

Epoxy binders take an important place in the world industry due to their production output and consumption level. They are widely used in different fields of application [1-6]. At the same time, they have some negative properties: high fragility, fire risk, low resistance to climatic factors [4-9].

One of the basic directions for development of epoxy composites with improved operational properties is to introduce different fillers into their compositions (basalt, talcum, chromite, metallic oxides, technogenic wastes from industrial enterprises). The fillers enable to decrease cost price of finished products considerably due to decreasing the cost of expensive binders and to impart different functional properties [2-9, 10].

Technogenic wastes from industrial enterprises are often used as dispersed fillers of epoxy resins. The authors of works [11-13] suggest to use fly ash which is a by-product of coal combustion at thermal power plants, as a filler for epoxy composites. The filler content ranged from 10% to 50%. The conducted researches proved that when fly ash is added into epoxy composite, tension strength increased as the amount of the filler was increased to the critical point (30%), and then decreased considerably.

Composite materials supplemented with microsilica have improved strength characteristics in comparison with polymer composites without the filler [14]. Eastomers introduction into epoxy resin increases their strength characteristics [15-16]. Literature analysis proved that due to fillers addition [17] into epoxy resin it is possible to improve some of its parameters.

The goal of the research is to study the impact of dispersed microsilica addition on chemical resistance of ED-20 epoxy-based polymer composite material, as well as on abrasion capacity and resistance to variable temperatures of ED-20 epoxy-based composite materials.

Experimental procedure

Epoxy-diane resin ED-20 (GOST 10587-84) was used as a binder for the produced compositions, as this resin is characterized by stability of dielectric and physical and chemical properties. Along with high thermal resistance, ED-20 is very fragile that can be improved by introducing special modifiers and solidifiers into composition.

Polyethylenepolyamine (TU 2413-010-75678843-2012) produced by research and production company "Astat" (Dzerzhinsk, Russia) was used as a solidifier. It is intended for solidifying epoxy resins at room and low temperatures under humid conditions. Solidifier appearance is as follows: a liquid, color is from light-yellow to dark-brown, without mechanical impurities.

To fill polymer compositions, microsilica was used («Tau-Ken Temir» Silicon Plant, Karaganda). Microsilica is formed in the process of silicon alloys (ferrosilicium) smelting. After oxidation and condensation some silicon monoxide form extremely small product in the shape of round particles with high content of amorphous silica [14].

Microsilica in the amounts 2, 5, 10 mas. % was added into epoxy resin and thoroughly blended for 5-10 minutes until uniform mass. Then the solidifier was added (*resin: solidifier* ratio is 1:10) and blended for 2 minutes. The resulted mass was applied by several thin layers on substrate in order to avoid bubbles in the samples. The check sample was made without adding the filler. It was solidified at room temperature for 24 hours. All the tests were carried out on samples of steel substrate 70×150 mm in size. Coating thickness was defined in compliance with ST RK GOST R 51694-2007. (Coating materials. Definition of coating thickness). Inaccuracy is $\pm 2 \mu\text{m}$. Table 1 provides coating samples thickness data.

Table 1 - Coatings thickness

№	Sample name	Thickness, μm
1	ED-20	16
2	ED-20 + 2% of microsilica	18
3	ED-20 + 5% of microsilica	17
4	ED-20 + 10% of microsilica	18

Chemical and elemental composition was defined on an x-ray fluorescent spectrometer produced by PANalytical, model Axios Max (Rh 2.4kW). Filler surface morphology was studied with scanning electron microscope TM 3030 (Hitachi). Filler particles size was defined with laser particle size analyzer Mastersizer 3000 with attachment Hydro MV (120 ml), water was used as dispersive medium.

X-ray diffraction was measured with the X-ray diffractometer SmartLab produced by Rigaku Corporation. X-radiation source is x-ray tube Cu $K\alpha$ -radiation (1.54059). Current and voltage of the tube are set at 50 mA and 40 kW respectively. One-dimensional detector (D/teX Ultra, Rigaku) with

Table 4 – Indexes of coating resistance to abrasion and resistance to variable temperatures impact of epoxy resin with different mass content of filler

№	Epoxy resin name	Coating resistance to abrasion	Resistance to variable temperatures impact
1	ED-20	0.056	Brightness and colour variations, flaking from the surface at temperature from (40±2)°C below zero up to (60±2)°C above zero (for 60) minutes haven't been found out
2	ED-20 + 2% of microsilica	0.044	Brightness and colour variations, flaking from the surface at temperature from (40±2)°C below zero up to (60±2)°C above zero (for 60 minutes) haven't been found out
3	ED-20 + 5% of microsilica	0.052	Brightness and colour variations, flaking from the surface at temperature from (40±2)°C below zero up to (60±2)°C above zero (for 60 minutes) haven't been found out
4	ED-20 + 10% of microsilica	0.036	Brightness and colour variations, flaking from the surface at temperature from (40±2)°C below zero up to (60±2)°C above zero (for 60 minutes) haven't been found out

The results provided in Table 4 indicate that appearance changes of epoxy resin samples with different mass content of fillers were not found out during their examining after variable temperatures impact: coating on the substrate is even, there is no flaking from the substrate, no visible defects and cracks. The test on coating resistance to abrasion showed that the samples supplemented with 2% of microsilica are mostly resistant to abrasion.

Conclusions

As it can be seen from the obtained data, after corrosive impact the samples supplemented with 2% of microsilica got the best indicators of preserving appearance and change of bond strength of coating to metal. Besides the amount of the filler from 2 to 10 mass % is insufficiently reflected in the resistance to variable temperatures

impact. When tests were completed, appearance changes weren't observed during epoxy resin samples examination after variable temperatures impact: homogeneous mass, coating on the substrate is even, there is no flaking from the substrate, no visible defects and cracks. When microsilica is added into epoxy resin, it causes the improvement of resistance to abrasion.

Thus, microsilica usage as a filler enables to produce epoxy materials with good chemical resistance, with high resistance to abrasion and variable temperatures impact.

Conflicts of interest. On behalf of all authors, the corresponding author states that there is no conflict of interest.

Acknowledgement. This study was funded by the Science Committee of the Ministry of Education and Science of the Republic of Kazakhstan (Grant №AP09058166).

Cite this article as: Serekpaeva M.A., Kokaeva G.A., Niyazbekova R.K., Kardymbaj S. Investigation of the properties of composite materials based on epoxy resins with microsilica additives. *Kompleksnoe Ispol'zovanie Mineral'nogo Syr'a. = Complex Use of Mineral Resources = Mineraldik Shikisattardy Keshendi Paidalanu.* 2021, Volume 3, Issue 318, pp. 63-70.

<https://doi.org/10.31643/2021/6445.29>

Микрокремнезем қоспалары бар эпоксидті шайырлар негізіндегі композициялық материалдардың қасиеттерін зерттеу

Серекпаева М.А., Кокаева Г.А., Ниязбекова Р.К., Кардыбай С.

С. Сейфуллин атындағы Қазақ Агротехникалық Университеті, Нур-Сұлтан қ, Қазақстан

ТҮЙІНДЕМЕ

Мақалада эпоксидті шайыр негізіндегі композициялық материалдарды зерттеу нәтижелері келтірілген. Толтырғыш ретінде микрокремнезем қолданылды. Үлгілер ЭД-20 эпоксидті шайыр

Мақала келді: 29 маусым 2021
 Сараптамадан өтті: 16 шілде 2021
 Қабылданды: 06 тамыз 2021

құрамына 2, 5, 10 мас. % микрокремнезем қосу арқылы жасалды. Ұсақ дисперсті толтырғыш бөлшектерінің құрылымы мен өлшемдері анықталды. Алынған композициялар ауыспалы температураға, агрессивті ортаға және үйкеліске төзімділікке тексерілді. Зерттеу нәтижелері көрсеткендей, 2% микрокремнезем қоспалары бар үлгілер 25% қышқыл мен сілтінің әсеріне, сондай-ақ бензиннің әсеріне төзімді. Бұл жағдайда толтырғыштың мөлшері 2-ден 10 мас. % болғанда айнымалы температураның әсеріне, төзімділікке айтарлықтай әсер етпейді. Эпоксидті шайырға кремнеземді енгізу үйкеліс төзімділігін арттырады. Өткізілген сынақтар әзірленген композициялық материалдардың ауыспалы температураға, агрессивті ортаға, үйкеліс әсеріне төзімділігін көрсетті, бұл оларды машиналарды жөндеу кезінде жабын және коррозияға қарсы қорғаныс ретінде пайдалануға мүмкіндік береді.

Түйін сөздер: Эпоксидті шайыр, микрокремнезем, толтырылған композициялық материал, химиялық төзімділік, композициялық материал, агрессивті орта, үйкеліс, жабын.

<i>Серекпаева Мира Амангельдиновна</i>	Авторлар туралы ақпарат: «Стандарттау, метрология және сертификаттау» кафедрасының докторанты, С.Сейфуллин атындағы Қазақ агротехникалық университеті, Нұр - Сұлтан, Қазақстан. E-mail: mika82.02@mail.ru.
<i>Кокаева Гульнара Айттикеновна</i>	Техника ғылымдарының кандидаты, «Технологиялық машиналар және жабдықтар» кафедрасының қауымдастырылған профессоры, С.Сейфуллин атындағы Қазақ агротехникалық университеті, Нұр - Сұлтан, Қазақстан. E-mail: GAKokaeva@mail.ru, https://orcid.org/0000-0001-9571-5081
<i>Ниязбекова Римма Калманбаевна</i>	Техника ғылымдарының докторы, «Стандарттау, метрология және сертификаттау» кафедрасының доценті, С.Сейфуллин атындағы Қазақ агротехникалық университеті, Нұр - Сұлтан, Қазақстан. E-mail: rimma.n60@mail.ru, ORCID ID: 0000-0001-8688-1408
<i>Кардыбай Саутбек</i>	«Технологиялық машиналар және жабдықтар» кафедрасының ассистенті, С.Сейфуллин атындағы Қазақ агротехникалық университеті, Нұр - Сұлтан, Қазақстан. E-mail: sautbek_kz@mail.ru

Исследование свойств композиционных материалов на основе эпоксидных смол с добавкой микрокремнезема

Серекпаева М.А., Кокаева Г.А., Ниязбекова Р.К., Кардыбай С.

Казахский Агротехнический Университет имени С. Сейфуллина, Нур-Султан, Казахстан

АННОТАЦИЯ

В статье приведены результаты исследований композиционных материалов на основе эпоксидной смолы. В качестве наполнителя использовали микрокремнезем. Образцы были изготовлены их эпоксидной смолы ЭД-20 с добавлением 2, 5 и 10 мас. % микрокремнезема. Определены структура и размеры частиц мелкодисперсного наполнителя. Полученные композиции исследовали на устойчивость к воздействию переменных температур, агрессивных сред и прочности к истиранию. Результаты исследований показали, что образцы с добавками 2% микрокремнезема более стойки к воздействию 25%-ных кислоты и щелочи, а также к действию бензина. При этом количество наполнителя от 2 до 10% мас. несущественно отражается на устойчивости к воздействию переменных температур. Введение микрокремнезема в эпоксидную смолу приводит к росту стойкости к истиранию. Проведенные испытания показали устойчивость разработанных композиционных материалов к воздействию переменных температур, агрессивных сред, стойкости к истиранию, что дает возможность использовать их в качестве покрытий и антикоррозионной защиты при ремонте машин.

Ключевые слова: эпоксидная смола, микрокремнезем, наполненный композиционный материал, химическая устойчивость, композиционный материал, агрессивная среда, истирание, покрытие.

Поступила: 29 июня 2021
 Рецензирование: 16 июля 2021
 Принята в печать: 06 августа 2021

<i>Серекпаева Мира Амангельдиновна</i>	Информация об авторах: – докторант кафедры «Стандартизация, метрология и сертификация», Казахский агротехнический университет имени С. Сейфуллина, Нур-Султан, Казахстан. E-mail: mika82.02@mail.ru
<i>Кокаева Гульнара Айттикеновна</i>	– кандидат технических наук, ассоциированный профессор кафедры «Технологические машины и оборудование», Казахский агротехнический университет имени С. Сейфуллина, Нур-Султан, Казахстан. E-mail: GAKokaeva@mail.ru, https://orcid.org/0000-0001-9571-5081
<i>Ниязбекова Римма Калманбаевна</i>	– доктор технических наук, доцент кафедры «Стандартизация, метрология и сертификация», Казахский агротехнический университет имени С. Сейфуллина, Нур-Султан, Казахстан. E-mail:

rimma.n60@mail.ru, ORCID ID: 0000-0001-8688-1408

Кардыбай Сауатбек

– ассистент кафедры «Технологические машины и оборудование», Казахский агротехнический университет имени С. Сейфуллина, Нур-Султан, Казахстан. E-mail: sautbek_kz@mail.ru

Литература

- [1] Starokadomskii D.L. (2017). Epoxy composites with 10 and 50 wt% micronanoiron: Strength, microstructure, and chemical and thermal resistance. *Russ. J. Appl. Chem.* 90, 1337-1345. <https://doi.org/10.1134/S1070427217080249>
- [2] Amirbeygi H., Khosravi H., Tohidlou E. (2019). Reinforcing effects of aminosilane-functionalized graphene on the tribological and mechanical behaviors of epoxy nanocomposites. *J. Appl. Polym. Sci.* 136, 47410. <https://doi.org/10.1002/app.47410>
- [3] Moaseri E., Bazubandi B., Baniadam M., Maghrebi M. (2019). Enhancement in mechanical properties of multiwalled carbon nanotube-reinforced epoxy composites: Crosslinking of the reinforcement with the matrix via diamines. *Polym. Eng. Sci.* 59, 1905-1910. <https://doi.org/10.1002/pen.25191>
- [4] Radoman T.S., Dzunuzovic J.V., Jeremic K.B., Grgur B.N., Milicevic D.S., Popovic I.G., Dzunuzovic E.S. (2014). Improvement of epoxy resin properties by incorporation of TiO₂ nanoparticles surface modified with gallic acid esters. *Mater. Des.* 62, 158-167. <https://doi.org/10.1016/j.matdes.2014.05.015>
- [5] Старокадомский Д. Л., Ткаченко А. А., Гаращенко И. И. (2017). Эпоксиполимерные композиции с 10–75 мас.% гипса: влияние наполнителя на прочность, термо-, химстойкость и оценка перспектив применения // *Химическая промышленность Украины*. № 6, 17-24.
- [6] Hu J.H., Shan J.Y., Wen D.H., Liu X.X., Zhao J.Q., Tong Z. (2014). Flame retardant, mechanical properties and curing kinetics of DOPO-based epoxy resins. *Polym. Degrad. Stab.* 109, 218-225. <https://doi.org/10.1016/j.polydegradstab.2014.07.026>
- [7] Mostovoi A.S., Yakovlev E.A., Burmistrov I.N., Panova L.G. (2015). Use of modified nanoparticles of potassium polytitanate and physical methods of modification of epoxy compositions for improving their operational properties. *Russ. J. Appl. Chem.* 88, 129-137. <https://doi.org/10.1134/S107042721501019X>
- [8] Mostovoy A.S., Kadykova Y.A., Bekeshev A.Z., Tastanova L.K. (2018). Epoxy composites modified with microfibers of potassium polytitanates. *J. Appl. Polym. Sci.* 135, 46651. <https://doi.org/10.1002/app.46651>
- [9] Mostovoy A.S., Nurtazina A.S., Kadykova Y.A., Bekeshev A.Z. (2019). Highly Efficient Plasticizers-Antipirenes for Epoxy Polymers. *Inorg. Mater. Appl. Res.* 10, 1135-1139. <https://doi.org/10.1134/S2075113319050228>
- [10] Mostovoy A.S., Nurtazina A.S., Burmistrov I.N., Kadykova Y.A. (2018). Effect of Finely Dispersed Chromite on the Physicochemical and Mechanical Properties of Modified Epoxy Composites. *Russ. J. Appl. Chem.* 91, 1758-1766. <https://doi.org/10.1134/S1070427218110046>
- [11] Feng L., Zhao H., He X., Zhao Y., Gou L., Wang Y. (2019). Synthesis and self-healing behavior of thermoreversible epoxy resins modified with nitrile butadiene rubber. *Polym. Eng. Sci.* 59, 1603–1610. <https://doi.org/10.1002/pen.25158>
- [12] Kulkarni S.M., Kishore. (2003). Effect of filler–fiber interactions on compressive strength of fly ash and short-fiber epoxy composites. *J. Appl. Polym. Sci.* 87, 836-841. <https://doi.org/10.1002/app.11501>
- [13] Singla M., & Chawla V. (2010). Mechanical properties of epoxy resin – fly ash composite. *Journal of Minerals & Materials Characterization & Engineering*, 9(3), 199-210. doi:10.4236/jmmce.2010.93017
- [14] Корнеев А.Д., Проскуракова А.О. (2011). Композиционный материал на основе пенополиуретана с использованием микрокремнезема // *Вестник Волгоградского государственного архитектурно-строительного. Сер.: Строительство и архитектура*. Вып. 24(43), 72-76.
- [15] Мейірбеков М.Н., Исмаилов М.Б. (2020). Влияние каучука на механические свойства эпоксидной смолы и углеродного волокна (Обзор) // *Kompleksnoe Ispol'zovanie Mineral'nogo syr'â/Complex Use of Mineral Resources/Mineraldik Shikisattardy Keshendi Paidalanu*, 1(312), 11-21. <https://doi.org/10.31643/2020/6445.02>
- [16] Mustafa L.M., Yermakhanova A.M., Ismailov M.B. (2019). The effect of carbon fabrics modification on the strength of carbon fiber reinforced plastic. // *Kompleksnoe Ispol'zovanie Mineral'nogo syr'â/Complex Use of Mineral Resources/Mineraldik Shikisattardy Keshendi Paidalanu*, №2, 68-75. <https://doi.org/10.31643/2019/6445.18>
- [17] Ермаханова А.М., Исмаилов М.Б. (2018). Влияние углеродных нанотрубок на процесс отверждения и прочность эпоксидной смолы // *Kompleksnoe Ispol'zovanie Mineral'nogo syr'â/Complex Use of Mineral Resources/Mineraldik Shikisattardy Keshendi Paidalanu*, №4, 105-114. <https://doi.org/10.31643/2018/6445.36>
- [18] ГОСТ 9.403 - 80 Единая система защиты от коррозии и старения. Покрытия лакокрасочные. Методы испытаний на стойкость к статическому воздействию жидкостей.

Reference

- [1] Starokadomskii D.L. (2017). Epoxy composites with 10 and 50 wt% micronanoiron: Strength, microstructure, and chemical and thermal resistance. *Russ. J. Appl. Chem.* 90, 1337-1345. <https://doi.org/10.1134/S1070427217080249> (in Eng.).

- [2] Amirbeygi H., Khosravi H., Tohidlou E. (2019). Reinforcing effects of aminosilane-functionalized graphene on the tribological and mechanical behaviors of epoxy nanocomposites. *J. Appl. Polym. Sci.* 136, 47410. <https://doi.org/10.1002/app.47410> (in Eng.).
- [3] Moaseri, E., Bazubandi B., Baniadam M., Maghrebi M. (2019). Enhancement in mechanical properties of multiwalled carbon nanotube-reinforced epoxy composites: Crosslinking of the reinforcement with the matrix via diamines. *Polym. Eng. Sci.* 59, 1905-1910. <https://doi.org/10.1002/pen.25191> (in Eng.)
- [4] Radoman, T.S., Dzunuzovic, J.V., Jeremic, K.B., Grgur, B.N., Milicevic, D.S., Popovic, I.G., Dzunuzovic, E.S. (2014). Improvement of epoxy resin properties by incorporation of TiO₂ nanoparticles surface modified with gallic acid esters. *Mater. Des.* 62, 158-167. <https://doi.org/10.1016/j.matdes.2014.05.015> (in Eng.).
- [5] Starokadomsky D.L., Tkachenko A.A., Garashchenko I.I. Epoksi-polimernye kompozicii s 10–75 mas. % gipsa: vliyanie napolnitelya na prochnost', termo-, himstojkost' i ocenka perspektiv primeneniya [Epoxy polymer compositions with 10–75 mas.% of gypsum: influence of the filler on strength, thermal and chemical resistance and assessment of application perspectives]. *Himicheskaya promyshlennost' Ukrainy/Chemical industry of Ukraine/Українська хімія өнеркәсібі.* 2017, 6, 17-24. (in Russ).
- [6] Hu, J.H., Shan, J.Y., Wen D.H., Liu X.X., Zhao J.Q., Tong Z. (2014). Flame retardant, mechanical properties and curing kinetics of DOPO-based epoxy resins. *Polym. Degrad. Stab.* 109, 218-225. <https://doi.org/10.1016/j.polymdegradstab.2014.07.026> (in Eng.).
- [7] Mostovoi A.S., Yakovlev E.A., Burmistrov I.N., Panova L.G. (2015). Use of modified nanoparticles of potassium polytitanate and physical methods of modification of epoxy compositions for improving their operational properties. *Russ. J. Appl. Chem.* 88, 129-137. <https://doi.org/10.1134/S107042721501019X> (in Eng.).
- [8] Mostovoy A.S., Kadykova Y.A., Bekeshev A.Z., Tastanova L.K. (2018) Epoxy composites modified with microfibers of potassium polytitanates. *J. Appl. Polym. Sci.* 135, 46651. <https://doi.org/10.1002/app.46651> (in Eng.).
- [9] Mostovoy A.S., Nurtazina A.S., Kadykova Y.A., Bekeshev A.Z. (2019). Highly Efficient Plasticizers-Antipirenes for Epoxy Polymers. *Inorg. Mater. Appl. Res.* 10, 1135-1139. <https://doi.org/10.1134/S2075113319050228> (in Eng.).
- [10] Mostovoy A.S., Nurtazina A.S., Burmistrov I.N., Kadykova Y.A. (2018). Effect of Finely Dispersed Chromite on the Physicochemical and Mechanical Properties of Modified Epoxy Composites. *Russ. J. Appl. Chem.* 91, 1758-1766. <https://doi.org/10.1134/S1070427218110046> (in Eng.).
- [11] Feng L., Zhao H., He X., Zhao Y., Gou L., Wang Y. (2019). Synthesis and self-healing behavior of thermoreversible epoxy resins modified with nitrile butadiene rubber. *Polym. Eng. Sci.* 59, 1603-1610. <https://doi.org/10.1002/pen.25158> (in Eng.).
- [12] Kulkarni S.M., Kishore. (2003). Effect of filler-fiber interactions on compressive strength of fly ash and short-fiber epoxy composites. *J. Appl. Polym. Sci.* 87, 836-841. <https://doi.org/10.1002/app.11501> (in Eng.).
- [13] Singla, M., & Chawla, V. (2010). Mechanical properties of epoxy resin – fly ash composite. *Journal of Minerals & Materials Characterization & Engineering*, 9(3), 199-210. doi:10.4236/jmmce.2010.93017. (in Eng.).
- [14] Korneyev A.D., Proskuryakova A.O. Kompozicionnyj material na osnove penopoliiuretana s ispol'zovaniem mikrokremlnezema [Composite material based on polyurethane foam with the use of microsilica]. *Vestnik Volgogradskogo gosudarstvennogo arhitekturno-stroitel'nogo universiteta/ Bulletin of the Volgograd State University of Architecture and Civil Engineering/Волгоград мемлекеттік сәулет-құрылыс университетінің хабаршысы. Ser.: Stroitel'stvo i arhitekturayu*, 2011, 24(43), 72-76. (in Russ).
- [15] Meyirbekov M.N., Ismailov M.B. liyanie kauchuka na mekhanicheskie svojstva epoksidnoj smoly i ugleplastika (Obzor) [Rubber impact on mechanical properties of epoxy resin and carbon fiber-reinforced plastic (Review)]. *Kompleksnoe Ispol'zovanie Mineral'nogo syr'â/Complex Use of Mineral Resources/Mineraldik Shikisattardy Keshendi Paidalanu*, 2020, 1(312), 11-21. <https://doi.org/10.31643/2020/6445.02> (in Russ).
- [16] Mustafa L.M., Yermakhanova A.M., Ismailov M.B. (2019) The effect of carbon fabrics modification on the strength of carbon fiber reinforced plastic. //Kompleksnoe Ispol'zovanie Mineral'nogo Syr'a/Complex Use of Mineral Resources. 2, 68-75. <https://doi.org/10.31643/2019/6445.18> (in Eng.).
- [17] Ermakhanova A.M., Ismailov M.B. Vliyanie uglerodnyh nanotrubok na process otverzheniya i prochnost' epoksidnoj smoly. [Influence of carbon nanotube on solidification process and epoxy resin strength]. *Kompleksnoe Ispol'zovanie Mineral'nogo syr'â/Complex Use of Mineral Resources/Mineraldik Shikisattardy Keshendi Paidalanu*, 2018, 4. 105-114. <https://doi.org/10.31643/2018/6445.36> (in Russ).
- [18] GOST 9.403 - 80 Edinaya sistema zashchity ot korrozii i stareniya. Pokrytiya lakorasochnyye. Metody ispytaniy na stojkost k staticheskomu vozdeystviyu zhidkostey. [Unified system of corrosion and ageing protection. Paint and coatings. Test method for resistance to liquids static effect]. (in Russ).